

HD High Performance High Concentrate Nano TiO₂ Sol BET surface area 240 m²/g

Special properties: <ul style="list-style-type: none"> • high concentration water-based nano TiO₂ sol • flow agglomeration, super fine particle size • high stability & quick gel feature • high surface area • high efficiency & performance 	Technical Information: <table border="1"> <tr> <td>Chemical description:</td> <td>Nano titanium dioxide slurry</td> </tr> <tr> <td>• appearance:</td> <td>White aqueous slurry</td> </tr> <tr> <td colspan="2">Active matter content:</td> </tr> <tr> <td>• TiO₂</td> <td>15 % (±2 %)</td> </tr> <tr> <td>• Water content:</td> <td>85 % +- 1%</td> </tr> <tr> <td>• Alcohol content:</td> <td>0%</td> </tr> </table>	Chemical description:	Nano titanium dioxide slurry	• appearance:	White aqueous slurry	Active matter content:		• TiO₂	15 % (±2 %)	• Water content:	85 % +- 1%	• Alcohol content:	0%		
Chemical description:	Nano titanium dioxide slurry														
• appearance:	White aqueous slurry														
Active matter content:															
• TiO₂	15 % (±2 %)														
• Water content:	85 % +- 1%														
• Alcohol content:	0%														
Example of application: <ul style="list-style-type: none"> • cosmetic additive (UV block, whiten, anti-bacterial, anti-allergen) • paint additive (deodorization, anti-moss, air purification) • dye sensitized solar battery • air purification system (coat on reaction part, filter, duct) 	Specification: <table border="1"> <tr> <td>• PH Value:</td> <td>PH 7,5 - 11,0</td> </tr> <tr> <td>• primary particle size:</td> <td>> 8 -11 nm</td> </tr> <tr> <td>• crystal structure:</td> <td>TiO₂ Anatasee</td> </tr> <tr> <td>• agglomeration index:</td> <td>> 20-30 %</td> </tr> <tr> <td>• density:</td> <td>1.08-1.11 g/ml</td> </tr> <tr> <td>• Viscosity:</td> <td>1.0050 mPa.s</td> </tr> <tr> <td>• BET surface area:</td> <td>BET 240 m²/g</td> </tr> </table>	• PH Value:	PH 7,5 - 11,0	• primary particle size:	> 8 -11 nm	• crystal structure:	TiO ₂ Anatasee	• agglomeration index:	> 20-30 %	• density:	1.08-1.11 g/ml	• Viscosity:	1.0050 mPa.s	• BET surface area:	BET 240 m ² /g
• PH Value:	PH 7,5 - 11,0														
• primary particle size:	> 8 -11 nm														
• crystal structure:	TiO ₂ Anatasee														
• agglomeration index:	> 20-30 %														
• density:	1.08-1.11 g/ml														
• Viscosity:	1.0050 mPa.s														
• BET surface area:	BET 240 m ² /g														
Usage instructions: <ul style="list-style-type: none"> • high speed cutting and mix up • roller print • Spinning coating • Dipping coating • air mix pressure spraying Dosage instruction: <ul style="list-style-type: none"> • refer to relevant coverage data sheet or product manual 	• Drying time at 25°C <table border="1"> <tr> <td>Primary drying time:</td> <td>30 minutes</td> </tr> <tr> <td>Final setting time:</td> <td>30 days</td> </tr> </table>	Primary drying time:	30 minutes	Final setting time:	30 days										
Primary drying time:	30 minutes														
Final setting time:	30 days														
Transport No Transport danger for Air, Sea, Highway and Rail, transportation of dangerous goods	Registration status: The ingredients are listed in the following chemical inventories: CAS, EINECS, TSCA, AICS, CEPA, MITI														
Storage stability: 12 months in closed container 5-45°C, dark condition. Protect Slurry in opened container from Oxygen. Avoid freezing! storind above 5°C	Package: 1 Kg, 10 Kg, 25Kg, Plastic barrel with carton 30 Kg, 100 Kg, 200 Kg Plastic / Polymer barrel * refer to relevant (MSDS) Material Safety Data Sheet														